

TECHNICAL DATA

Water Vapour Transmission(g/m2 ; 24h, ≤)	7.35
Water Tightness (2500mm, 2h)	Pass
Maximum Tensile Force (MD) (N/50mm,≥)	430
Maximum Tensile Force (XD) (N/50mm, ≥)	374
Resistance to Tearing MD (Nail Shank) (N, ≥)	123
Resistance to Tearing XD (Nail Shank) (N, ≥)	101
Tensile Strength after Ageing (MD) (% ,≥)	80
Tensile Strength after Ageing (XD) (% ,≥)	80
Resistance to Water Penetration after Ageing (% ,≥)	80
UV Resistance (Days)	180

Remark: ARKINT Products can meet or exceed the following code standards: ASTM D1970, ASTM D226, ASTM D4869, CAN/CSA A123.3, Class A Fire - ASTM E108, etc.

TECHNICAL SERVICES

Technical information and detailed test results can be obtained by emailing the manufacturer at info@arksynthetics.com Tel: 778 325 1557

