

TECHNICAL DATA

UV Resistance	ASTM G154	3 Months
Tensile strength MD CD	ASTM D1970	75 lbf/in 65 lbf/in
Elongation	ASTM D1970	>60%
Tear strength MD CD	ASTM D1970	70 lbf 65 lbf
Adhesion to plywood @75°F @40°F	ASTM D1970	75 lbf/ft 65 lbf/ft
Adhesion to metal @75F @40°F	ASTM D1970	85 lbf/ft 80 lbf/ft
Adhesion to gypsum @75F @40°F	ASTM D1970	70 lbf/ft 65 lbf/ft
Lap Adhesion	ASTM D1876	75 lbf/ft
Nail Sealability	ASTM D1970	Pass
Thermal stability	ASTM D1970	275° F (135° C)
Permeability	ASTM E96	<0.05 Perms
Installation Temperature		25°F (-4°C) and rising
Low Temperature Flexibility	ASTM D5147	Pass
Limited Warranty		Lifetime

TECHNICAL SERVICES

Technical information and detailed test results can be obtained by emailing the manufacturer at info@arksynthetics.com Tel: 778 325 1557

