

TECHNICAL DATASHEET

Ark G1

**Glass Wool Slab
Formaldehyde Free**

THICKNESS	WIDTHS	LENGTHS	DENSITY
25-100mm	0.6-2.4m	0.6m-1.2m	24-96kg/m ³
1"-4"	24"-95"	24"-47"	1.5pcf-6pcf

Property	Test Method	Value
Operating Temperature Range	ASTM C411	L Series: up to 1000B°F (538B°C) HP5 II Mat: up to 1100B°F (593B°C)
Corrosion Resistance	ASTM C665	Meets requirement
Fungi Resistance	ASTM C1338	Meets requirements
Odor	ASTM C1304	No objectionable odor
Moisture Sorption	ASTM C1104	< 3% by weight
Composite Surface Burning Characteristics Flame Spread Smoke Developed ⁴	ASTM E84, UL 723, and CAN/ULC-S102	< 25 < 50

Note: Customized specification available!

Email: info@devreltech.com Phone: +86 18518513606

Add: Room 210, Building 2, Yard 1, Kechuang 13 Street, Yizhuang, Daxing District, Beijing, China

www.Devreltech.com