

TECHNICAL DATA

UV Resistance	ASTM G154	3 Months
Tensile strength MD CD	ASTM D1970	120 lbf/in 115 lbf/in
Elongation	ASTM D1970	>90%
Tear strength MD CD	ASTM D1970	120 lbf 105 lbf
Adhesion to plywood @75°F @40°F	ASTM D1970	55 lbf/ft 23 lbf/ft
Adhesion to metal @75°F @40°F	ASTM D1970	67 lbf/ft 51 lbf/ft
Adhesion to gypsum @75°F @40°F	ASTM D1970	70 lbf/ft 65 lbf/ft
Lap seam, waterproof integrity	ASTM D1970	Pass
Nail Sealability	ASTM D1970	Pass
Tear resistance MD / CD	ASTM D4869	140 lbf 120 lbf
Permeability	ASTM E96	<0.05 Perms
Thermal stability		265°F (129.4°C)
Low Temperature Flexibility	ASTM D5147	Pass
Limited Warranty		Lifetime

Remark: ARKINT Products can meet or exceed the following code standards: ASTM D1970, ASTM D226, ASTM D4869, CAN/CSA A123.3, Class A Fire - ASTM E108, etc.

TECHNICAL SERVICES

Technical information and detailed test results can be obtained by emailing the manufacturer at info@arksynthetics.com Tel: 778 325 1557

