

FACING COMPOSITION	DESCRIPTION	VALUES(ENGLISH)	VALUES(METRIC)
Foil	Aluminum	0.00026 inch	6.5µm
Adhesive	Adhesive		
Reinforcing	Tri-Directional Fiberglass	2 / inch (MD) 3 / inch (XD)	8/100 mm (MD) 12/100 mm (XD)
Kraft	Natural	43 lbs / 3000 ft ²	70g/ m ²
Backing	PE	15 lbs / 3000 ft ²	25g/ m ²
PHYSICAL PROPERTIES	TEST METHOD	VALUES(ENGLISH)	VALUES(METRIC)
Basis Weight	Scale	27 lbs /1000 ft ²	132 g/ m ²
Permeance (WVTR)	ASTM E96/Procedure A	0.02 perm	1.15ng/N.s
Tensile Strength	ASTM C1136	44 lbs/inch (MD) 31 lbs/inch (XD)	7.64kN/m (MD) 5.4kN/m (XD)
Thickness	Micrometer Caliper	0.008 inch	200 micron
Fire Rating	ASTM E84	Class B	Class B
Accelerated Aging	ASTM C1258 30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F(-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F(116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Dimensional Stability	ASTM D1204	0.25%	0.25%
Emissivity	ASTM E408	0.03	0.03

TECHNICAL SERVICES

Technical information and detailed test results can be obtained by emailing the manufacturer at info@arksynthetics.com Tel: 778 325 1557

