

FACING COMPOSITION	DESCRIPTION	VALUES(ENGLISH)	VALUES(METRIC)
White Film	FR Polypropylene	0.00071 inch	18µm
Adhesive	Flame Retardant		
Reinforcing	Tri-Directional Fiberglass	2 / inch (MD) 3 / inch (XD)	8/100 mm (MD) 12/100 mm (XD)
Kraft	Flame Retardant	43 lbs / 3000 ft ²	70g/ m ²
PHYSICAL PROPERTIES	TEST METHOD	VALUES(ENGLISH)	VALUES(METRIC)
Basis Weight	Scale	19lbs /1000 ft ²	95g/ m ²
Permeance (WVTR)	ASTM E96/Procedure A	0.09 perm	5.5ng/N.s
Tensile Strength	ASTM C1136	34 lbs/inch (MD) 30 lbs/inch (XD)	6.0kN/m (MD) 5.2kN/m (XD)
Thickness	Micrometer Caliper	0.006 inch	160 micron
Fire Rating	ASTM E84	Class A	Class A
Accelerated Aging	ASTM C1258 30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F(-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F(116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Dimensional Stability	ASTM D1204	0.25%	0.25%
Emissivity	ASTM E408	0.03	0.03

TECHNICAL SERVICES

Technical information and detailed test results can be obtained by emailing the manufacturer at info@arksynthetics.com Tel: 778 325 1557

